

FERRO TONDO PER CEMENTO ARMATO IN BARRE AD ADERENZA MIGLIORATA



Diametro	Peso	Sezione in cm ² per numero di barre				
mm	Kg/ml	1	2	3	4	5
8	0,395	0,503	1,005	1,508	2,010	2,513
10	0,617	0,785	1,571	2,356	3,141	3,926
11	0,746	0,950	1,907	2,851	3,801	4,751
12	0,888	1,131	2,262	3,393	4,524	5,564
14	1,210	1,539	3,079	4,618	6,157	7,696
16	1,580	2,011	4,021	6,032	8,042	10,053
18	2,000	2,545	5,089	7,634	10,178	12,723
20	2,470	3,141	6,283	9,424	12,566	15,707
22	2,980	3,801	7,602	11,403	15,204	19,005
24	3,550	4,523	9,096	13,569	18,092	22,015
26	4,170	5,310	10,020	15,930	21,240	26,550
28	4,830	6,157	12,314	18,471	24,628	30,785
30	5,550	7,068	14,136	21,204	28,272	35,340

